VMS Carbon
Activated carbon suppliers
+91 92741 73384 · sales@vmscarbon.com
vmscarbon.com

TECHNICAL DATA SHEET

Product name: Pelletized activated carbon

Pellet

Even cylindrical pellets that let air and gas pass with a low pressure drop. The values below are the typical properties of this grade, measured in our laboratory by the test methods shown. Every production batch is tested before dispatch and ships with its own test report carrying the batch number; the values for your order are confirmed with the quote.

Parameter	Test method	Typical value
Diameter	—	**3 mm or 4 mm**
CTC	ASTM D3467	**50 to 70%**
Hardness	ASTM D3802	**95% min**
Ash	ASTM D2866	**8 to 12%**
Moisture	ASTM D2867	**5% max**

Packing: 25 kg bags

Storage: Keep dry, in the closed bags, away from strong oxidisers and solvent vapours.

Values are typical and are not a specification for every lot; the test report of each batch gives its measured values.

Checked by

Quality control
VMS Carbon

Date: 13 November 2026

Stamp and signature